

**50 µm PP-Film glossy erasable  
with electrostatic charge.**

# FOLIOCONTACT

## Simply Notes 1.0

### Description:

FOLIOCONTACT SIMPLY NOTES is an environmental friendly Flip-Chart Media, made of Polypropylen. It has been developed and been produced by NOPAR INTERNATIONAL INC. and patented under: EP 1326918 B1.

FOLIOCONTACT SIMPLY NOTES is a special produced 3-layer coex cast PP-Film. The mid Layer is able to take on ionisation and keep it for at least 5 Years, depending on the storage conditions, packed and boxed at 40-50% rel. humidity, at 18°-22°C.

The sheets are available in the sizes of 10x10cm and 10x20cm, with 5 different colours: pink, green, white, yellow and blue. Every package contains 100 sheets. Each sheet adhere to virtually any surface without any other tools, such as adhesive or pins disputes.

The film is ideally suited for use with non-permanent, or dry erase whiteboard markers. When using permanent markers, it will be not possible to clean the film surface again, except when alcoholic cleaning solution is taken (please care about dangerous Goods Regulations).

For further details please contact NOPAR INTERNATIONAL INC.



### Applications:

FOLIOCONTACT SIMPLY NOTES can be used for:

- sticky notes
- on every smooth surfaces:
- including doors, windows, cupboards

### Compatibility:

FOLIOCONTACT SIMPLY NOTES is not made for printing or individual printed artworks.

FOLIO CONTACT SIMPLY NOTES can be recycled, be disposed with the yellow bag and capable for energy recovery. Safety data sheets can be requested if necessary.

### Spezification:

Requirement	Worth	Limit	Unit	Methode	Requirement	Worth	Limit	Unit	Methode
Grammage total	246	±12	g/m <sup>2</sup>	ISO 536	Glance 60°	>20	--	%	ISO 2813
Grammage liner	158	±7%	g/m <sup>2</sup>	DIN EN ISO 536	Opacity w/o liner	>85		%	2471
Thickness total	256	±15	µm	ISO 534	Colour (D50 2°), L*	95	Delta E<3,0	--	DIN ISO 13655, X-Rite 528
Thickness liner	150	±9%	µm	DIN EN 20534	a*	0,1		--	DIN ISO 13655, X-Rite 528
Bending strength md	717	±20%	mN	ISO 4293; L&W (15°/10mm)	b*	-3,8		--	DIN ISO 13655, X-Rite 528
Bending strength cd	660	±20%	mN	ISO 4293; L&W (15°/10mm)	CIE whiteness (D65/10°)	113	±10	--	ISO 11475, PTA 40600
Adhesion strength	30-100		cN/50mm	FTM 3	Adhesive-temperature	15-45°C			
Durability	at least 2 years after delivery, be in the original packaging in storage under 35-65 % r.F. and at 10-30°C								

Any reproduction or use of this publication or partially reproduced information in electronic or printed form is prohibited without written Permission and acknowledgment by the owner  
NOPAR International GmbH



# NOPAR INTERNATIONAL

NOPAR International GmbH  
Ladestrasse 3-3a  
28197 Bremen/Germany  
Phone: +49 421 5208146 0  
Fax: +49 421 5208146 9  
Mail: info@nopar-international.com  
Web: www.nopar-international.com

Please note that all information supplied is correct to date of print, information. It can change without prior notification. This information does not release the manufacturer from his obligation with regard to proper application and handling of the product. All content is based on available technical knowledge at the time of publication.

Published in January 2018